

# Trademark PE LD0720C

Low Density Polyethylene  
Trademark Plastics Corporation

Message:

Trademark PE LD0720C is a Low Density Polyethylene product. It is available in North America. Applications of Trademark PE LD0720C include bags/liners, film, food contact applications and wrap.

Characteristics include:

Antiblock  
Food Contact Acceptable  
Good Processability  
Good Toughness

General Information			
Additive	Antiblock		
Features	Additive Free		
	Antiblocking		
	Food Contact Acceptable		
	Good Drawdown		
	Good Processability		
	Good Toughness		
Uses	Film		
	Heavy-duty Bags		
	Liners		
	Shrink Wrap		
Agency Ratings	FDA 21 CFR 177.1520(c) 2.1		
Physical	Nominal Value	Unit	Test Method
Density	0.920	g/cm³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.70	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	51	µm	ASTM D882
Secant Modulus			
1% Secant, MD : 51 µm, Blown Film	172	MPa	
1% Secant, TD : 51 µm, Blown Film	217	MPa	ASTM D882
Tensile Strength			
MD : Break, 51 µm,Blown Film	23.4	MPa	
TD : Break, 51 µm,Blown Film	16.5	MPa	ASTM D882
Tensile Elongation			
MD : Break, 51 µm,Blown Film	170	%	
TD : Break, 51 µm,Blown Film	490	%	

Dart Drop Impact (51 μm, Blown Film)	130	g	ASTM D1709
Elmendorf Tear Strength			ASTM D1922
MD : 51 μm, Blown Film	290	g	
TD : 51 μm, Blown Film	180	g	
Optical	Nominal Value	Unit	Test Method
Haze (50.8 μm, Blown Film)	11	%	ASTM D1003
Extrusion	Nominal Value	Unit	
Melt Temperature	182 to 199	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

