ADDINYL C2 V20

Polyamide 66/6 Copolymer

ADDIPLAST

Message:

ADDINYL C2 V20 is a Polyamide 66/6 Copolymer (Nylon 66/6) material filled with 20% glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, or Latin America. Primary attribute of ADDINYL C2 V20: Rigid.

Typical applications include:

General Information

Automotive

Appliances

Electrical/Electronic Applications

Housings

| General information | | | | | | |
|---------------------------------------------------|--------|------------------------------------|----------|-------------|--|--|
| Filler / Reinforcement | | Glass Fiber,20% Filler by Weight | | | | |
| Features | | High Rigidity | | | | |
| Uses | | Appliance Components | | | | |
| | | Automotive Applications | | | | |
| | | Automotive Interior Parts | | | | |
| | | Electrical/Electronic Applications | | | | |
| | | Housings | | | | |
| | | | | | | |
| Forms | | Pellets | | | | |
| Physical | Dry | Conditioned | Unit | Test Method | | |
| Density | 1.29 | | g/cm³ | ISO 1183/A | | |
| Hardness | Dry | Conditioned | Unit | Test Method | | |
| Shore Hardness (Shore D) | 84 | 78 | | ISO 868 | | |
| Mechanical | Dry | Conditioned | Unit | Test Method | | |
| Tensile Stress (Break) | 130 | 80.0 | MPa | ISO 527-2 | | |
| Tensile Strain (Break) | 4.0 | 7.0 | % | ISO 527-2 | | |
| Flexural Modulus | 5600 | 3400 | MPa | ISO 178 | | |
| Impact | Dry | Conditioned | Unit | Test Method | | |
| Charpy Notched Impact Strength | 6.0 | 11 | kJ/m² | ISO 179/1eA | | |
| Charpy Unnotched Impact Strength | 45 | 50 | kJ/m² | ISO 179/1eU | | |
| Notched Izod Impact | | | | | | |
| Strength | 9.0 | 16 | kJ/m² | ISO 180/1A | | |
| Thermal | Dry | Conditioned | Unit | Test Method | | |
| Heat Deflection Temperature (1.8 MPa, Unannealed) | 230 | | °C | ISO 75-2/Af | | |
| | | | °C | ISO 3146 | | |
| Melting Temperature (DSC) | 243 | | | | | |
| CLTE - Flow | 4.5E-5 | | cm/cm/°C | ASTM E831 | | |
| Electrical | Dry | Conditioned | Unit | Test Method | | |

| Volume Resistivity | 1.0E+15 | 1.0E+12 | ohms·cm | IEC 60093 |
|----------------------|---------|---------|---------|-------------|
| Electric Strength | 33 | 30 | kV/mm | IEC 60243-1 |
| Comparative Tracking | | | | |
| Index (Solution A) | 600 | | V | IEC 60112 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

