

WPP PP M 2097-004

Polypropylene Impact Copolymer

Washington Penn Plastic Co. Inc.

Message:

Properties shown below for an extrusion grade high-impact copolymer polypropylene.

General Information			
Features	Rigid, good		
	Copolymer		
	Impact resistance, high		
Appearance	Available colors		
Forms	Particle		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.900	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	2.5	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	25.0	MPa	ASTM D638
Tensile Elongation ² (Break)	900	%	ASTM D638
Flexural Modulus ³	1050	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	750	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	94.0	°C	ASTM D648
Additional Information			
Tested at 23 ± 2°C (73.4 ± 3.6°F) and 50 ± 5% relative humidity unless otherwise noted			
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

