# ADMER™ NE062E

## Polyethylene

## Mitsui Chemicals Europe GmbH

#### Message:

ADMER® NE062E is an maleic anhydride grafted, PE-based adhesive designed for multilayer plastic pipes composed of PE, PEX, PE-RT and Aluminum. It offers advanced adhesion durability, high heat resistance and good processability.

General Information				
Features	Durable			
	Food Contact Acceptable			
	Good Adhesion			
	Good Processability			
	High Heat Resistance			
Uses	Adhesives			
	Food Service Applications			
	Non-specific Food Applications			
	Piping			
Agency Ratings	FDA 21 CFR 175.105			
Processing Method	Extrusion			
Physical	Nominal Value	Unit	Test Method	
Density	0.910	g/cm³	ASTM D1505	
Melt Mass-Flow Rate (MFR) (190°C/2.16				
kg)	4.5	g/10 min	ASTM D1238	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore D)	46		ASTM D2240	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength			ASTM D638	
Yield	8.00	MPa		
Break	19.0	MPa		
Tensile Elongation (Break)	> 500	%	ASTM D638	
Impact	Nominal Value	Unit	Test Method	
Unnotched Izod Impact (Area)	No Break		ASTM D256	
Thermal	Nominal Value	Unit	Test Method	
Vicat Softening Temperature	83.0	°C	ASTM D1525	
Peak Melting Temperature	122	°C	ASTM D3418	
Oxidation Induction Time (210°C)	65	min	ISO 11357-6	
Extrusion	Nominal Value	Unit		
Cylinder Zone 1 Temp.	180 to 200	°C		
Cylinder Zone 2 Temp.	180 to 200	°C		

Cylinder Zone 3 Temp.	200 to 230	°C	
Cylinder Zone 4 Temp.	200 to 230	°C	
Melt Temperature	200 to 230	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

