

Grilon® TSC-30/4 LF 15 black 9832

Polyamide 66/6 Copolymer

EMS-GRIVORY

Message:

Grilon® TSC-30/4 LF 15 black 9832 is a Polyamide 66/6 Copolymer (Nylon 66/6) material filled with 30% carbon fiber. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America for injection molding.

Important attributes of Grilon® TSC-30/4 LF 15 black 9832 are:

Flame Rated

RoHS Compliant

Antistatic

Conductive

Lubricated

Typical applications include:

Appliances

Automotive

Consumer Goods

Electrical/Electronic Applications

Engineering/Industrial Parts

General Information				
Filler / Reinforcement		Carbon Fiber,30% Filler by Weight		
Additive		Antistatic		
		Lubricant (15%)		
Features		Antistatic		
		Electrically Conductive		
		Good Wear Resistance		
		Low Friction		
		Lubricated		
Uses		Appliance Components		
		Automotive Applications		
		Consumer Applications		
		Electrical/Electronic Applications		
		Engineering Parts		
		Industrial Applications		
		Power/Other Tools		
		Sporting Goods		
RoHS Compliance		RoHS Compliant		
Appearance		Black		
Forms		Granules		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method

Density	1.40	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	0.10	--	%	
Flow	0.10	--	%	
Water Absorption				ISO 62
Saturation, 23°C	5.0	--	%	
Equilibrium, 23°C, 50% RH	1.5	--	%	
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness	210	120	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	23000	16000	MPa	ISO 527-2
Tensile Stress (Break)	230	170	MPa	ISO 527-2
Tensile Strain (Break)	2.5	4.5	%	ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	7.0	7.0	kJ/m ²	
23°C	10	13	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	45	45	kJ/m ²	
23°C	45	60	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
1.8 MPa, Unannealed	235	--	°C	ISO 75-2/A
8.0 MPa, Unannealed	130	--	°C	ISO 75-2/C
Continuous Use Temperature				Internal Method
-- ¹	90.0 to 120	--	°C	
-- ²	200	--	°C	
Melting Temperature ³	260	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow	1.0E-5	--	cm/cm/°C	
Transverse	8.0E-5	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	--	1.0E+3	ohms	IEC 60093
Volume Resistivity	1.0E+5	1.0E+5	ohms·cm	IEC 60093
Flammability	Dry	Conditioned	Unit	Test Method
Flammability Classification (0.800 mm)	HB	--		IEC 60695-11-10, -20
Additional Information	Dry	Conditioned		Test Method
ISO Type	PA 66+PA 6, MHRS, 14-220 N, CF30+Z15			ISO 1874

NOTE

- | | |
|----|------------|
| 1. | Long Term |
| 2. | Short Term |
| 3. | 10°C/min |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

