# ISORENE<sup>™</sup> AA6C1-1001

## Thermoplastic Elastomer

### SABIC Innovative Plastics Europe

#### Message:

ISORENE AA6C1-1001 is a special compound designed to be used in co-injection molding or coextrusion with SAN, ABS, PBT, PC or blends of these materials.

The value listed as Strain at Break, ISO 527, was tested in accordance with ISO 37. The value listed as Stress at Break, ISO 527, was tested in accordance with ISO 37.

General Information	
Forms	Pellets
Processing Method	Coextrusion
	Injection Molding

Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm³	ISO 1183
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	63		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	5.30	MPa	ISO 527-2
Tensile Strain (Break)	500	%	ISO 527-2
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ISO 37
100% Strain	2.80	MPa	
200% Strain	3.40	MPa	
300% Strain	4.00	MPa	
Tear Strength	22	kN/m	ISO 34-1

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

