

Lucet® HI-520

Acetal (POM) Copolymer

LG Chem Ltd.

Message:

Lucet® HI-520 is an Acetal (POM) Copolymer material. It is available in North America for injection molding.

Important attributes of Lucet® HI-520 are:

Flame Rated

Chemical Resistant

Copolymer

Creep Resistant

Good Dimensional Stability

General Information			
Additive	Impact Modifier		
Features	Copolymer		
	Good Abrasion Resistance		
	Good Chemical Resistance		
	Good Creep Resistance		
	Good Dimensional Stability		
	Good Impact Resistance		
	Good Moldability		
	Good Thermal Stability		
	Impact Modified		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.36	g/cm ³	ASTM D792
Molding Shrinkage - Flow	2.0 to 2.2	%	ASTM D955
Water Absorption (24 hr)	0.20	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	39.2	MPa	ASTM D638
Tensile Elongation (Break)	150	%	ASTM D638
Flexural Modulus	1180	MPa	ASTM D790
Flexural Strength (Yield)	49.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-40°C	98	J/m	
23°C	250	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	125	°C	

1.8 MPa, Unannealed	75.0	°C	
CLTE - Flow	1.0E-4	cm/cm/°C	ASTM D696
Flammability	Nominal Value		Test Method
Flame Rating (0.794 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 100	°C	
Drying Time	3.0 to 6.0	hr	
Rear Temperature	160 to 180	°C	
Middle Temperature	180 to 200	°C	
Front Temperature	190 to 200	°C	
Nozzle Temperature	190 to 210	°C	
Processing (Melt) Temp	190 to 200	°C	
Mold Temperature	60.0 to 80.0	°C	
Injection Pressure	39.2 to 68.6	MPa	
Back Pressure	3.92 to 7.84	MPa	
Screw Speed	50 to 100	rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

