

ALTECH® PP-B A 2040/150 GF40

Polypropylene Copolymer

ALBIS PLASTIC GmbH

Message:

ALTECH®PP-B A 2040/150 GF40 is a polypropylene copolymer (PP Copoly) product, which contains a 40% glass fiber reinforced material. It can be processed by injection molding and is available in North America, Europe or the Asia-Pacific region. ALTECH®The application fields of PP-B A 2040/150 GF40 include construction applications, electrical/electronic applications and engineering/industrial accessories.

Features include:

Comply with REACH standard

ROHS certification

Copolymer

Chemical coupling

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 40% filler by weight		
Features	Copolymer		
	Chemical coupling		
Uses	Electrical/Electronic Applications		
	Machine/mechanical parts		
	Building materials		
	Architectural application field		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS compliance		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.21	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	5.00	cm³/10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	7800	MPa	ISO 527-2
Tensile Stress	70.0	MPa	ISO 527-2
Tensile Strain (Break)	4.0	%	ISO 527-2
Flexural Stress	115	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	20	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength	65	kJ/m²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	145	°C	ISO 75-2/A
Vicat Softening Temperature	115	°C	ISO 306/B50
Injection	Nominal Value	Unit	


Drying Temperature		
Dehumidification desiccant	80 - 120	°C
Hot air dryer	80 - 120	°C
Drying Time		
Dehumidification desiccant	2.0 - 4.0	hr
Hot air dryer	2.0 - 3.0	hr
Processing (Melt) Temp	200 - 270	°C
Mold Temperature	20 - 90	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT