

TOTAL Polypropylene PPC 5947WZ

Polypropylene Impact Copolymer

TOTAL Refining & Chemicals

Message:

Total Petrochemicals Polypropylene 5947WZ is an impact copolymer with a Melt Flow of 105 g/10min. 5947WZ is characterized by excellent stiffness and impact resistance, excellent antistatic properties, as well as extremely good flow properties to allow faster cycling through early demolding. 5947WZ complies with all applicable FDA regulations for food contact applications. 5947WZ has been developed for high-speed injection molding of thin-walled packaging containers and household articles.

General Information			
Features	Antistatic		
	Fast Molding Cycle		
	Food Contact Acceptable		
	High Flow		
	High Impact Resistance		
	High Stiffness		
	Impact Copolymer		
Uses	Household Goods		
	Thin-walled Parts		
Agency Ratings	EC 1907/2006 (REACH)		
	FDA Unspecified Rating		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.905	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	110	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	25.0	MPa	ASTM D638
Tensile Elongation (Yield)	6.0	%	ASTM D638
Flexural Modulus	1300	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	80	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	110	°C	ASTM D648
Melting Temperature	160 to 165	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

