

Gebalon PC ULtimate G15 FR(y)

Polycarbonate

geba Kunststoffcompounds GmbH

Message:

15% GF, halogen-free flame retardant PC type, UL94-V0, UL recognized and evaluated by UL to UL94 V0

Applications:

technical injection molded parts, in particular the electronics and electrical industry, such as connectors, boxes, switches

General Information			
Filler / Reinforcement	Glass Fiber, 15% Filler by Weight		
Features	Flame Retardant		
	Halogen Free		
Uses	Connectors		
	Electrical/Electronic Applications		
	Switches		
UL File Number	E346354		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.30	g/cm ³	ISO 1183
Molding Shrinkage	0.20 to 0.70	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	4900	MPa	ISO 527-2/1/1
Tensile Stress (Yield)	90.0	MPa	ISO 527-2/50
Tensile Strain (Yield)	3.5	%	ISO 527-2/50
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	9.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	55	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	141	°C	ISO 75-2/B
1.8 MPa, Unannealed	137	°C	ISO 75-2/A
Vicat Softening Temperature	141	°C	ISO 306/B50
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.50 mm	V-0		
3.00 mm	V-0		
Glow Wire Ignition Temperature (1.50 mm)	960	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	
Drying Temperature - Dry Air Dryer	100 to 120	°C	

Drying Time - Dry Air Dryer	2.0 to 4.0	hr
Suggested Max Moisture	0.020	%
Rear Temperature	260 to 280	°C
Middle Temperature	280 to 310	°C
Front Temperature	290 to 320	°C
Nozzle Temperature	290 to 320	°C
Processing (Melt) Temp	290 to 320	°C
Mold Temperature	100 to 120	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

