

Ultramid® 8333G HI HS BK-102

Polyamide 6

BASF Corporation

Message:

Ultramid 8333G HI HS BK-102 is a 33% glass reinforced, impact modified PA6 injection molding compound pigmented black developed for applications requiring improved dry as molded toughness in combination with a balance of strength, stiffness and excellent moldability/surface aesthetics.

Applications

Ultramid 8333G HI HS BK-102 is generally recommended for application such as front wheel chair wheels, bicycle wheels, power tool housings, chain saw housings, clips and fasteners, hose clamps and window hardware.

General Information				
UL YellowCard		E36632-231152		
Filler / Reinforcement		Glass Fiber,33% Filler by Weight		
Additive		Impact Modifier		
Features		Good Moldability		
		Good Stiffness		
		Good Strength		
		Impact Modified		
Uses		Fasteners		
		Housings		
		Power/Other Tools		
		Wheels		
Agency Ratings		EC 1907/2006 (REACH)		
RoHS Compliance		RoHS Compliant		
Appearance		Black		
Forms		Pellets		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.34	--	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage - Flow (3.18 mm)	0.30	--	%	
Water Absorption				
24 hr	0.90	--	%	ASTM D570
23°C, 24 hr	0.90	--	%	ISO 62
Saturation	5.5	--	%	ASTM D570
Saturation, 23°C	5.5	--	%	ISO 62
Equilibrium, 50% RH	1.5	--	%	ASTM D570
Equilibrium, 23°C, 50% RH	1.5	--	%	ISO 62
Hardness	Dry	Conditioned	Unit	Test Method

Rockwell Hardness (R-Scale)	121	--		ASTM D785
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	9100	4610	MPa	ISO 527-2
Tensile Strength				
Break, 23°C	150	90.0	MPa	ASTM D638
Break, 23°C	140	90.0	MPa	ISO 527-2
Tensile Elongation				
Break, 23°C	3.0	--	%	ASTM D638
Break, 23°C	3.0	6.0	%	ISO 527-2
Flexural Modulus				
23°C	8140	--	MPa	ASTM D790
23°C	7500	5030	MPa	ISO 178
Flexural Strength				
23°C	240	--	MPa	ASTM D790
23°C	210	120	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179
-30°C	10	--	kJ/m ²	
23°C	18	--	kJ/m ²	
Charpy Unnotched Impact Strength (23°C)				ISO 179
	71	--	kJ/m ²	
Notched Izod Impact				
-40°C	110	--	J/m	ASTM D256
23°C	210	--	J/m	ASTM D256
-40°C	13	--	kJ/m ²	ISO 180
23°C	19	--	kJ/m ²	ISO 180
Drop Impact Resistance (23°C)				
	5.29	--	J	Internal Method
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	220	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	210	--	°C	ASTM D648
1.8 MPa, Unannealed	205	--	°C	ISO 75-2/A
Peak Melting Temperature	220	--	°C	ASTM D3418, ISO 3146
RTI Elec				UL 746
0.800 mm	140	--	°C	
1.50 mm	140	--	°C	
3.00 mm	140	--	°C	
RTI Imp				UL 746
1.50 mm	115	--	°C	
3.00 mm	120	--	°C	

RTI Str			UL 746
0.800 mm	130	--	°C
1.50 mm	140	--	°C
3.00 mm	140	--	°C
Flammability	Dry	Conditioned	Test Method
Flame Rating			UL 94
0.800 mm	HB	--	
1.50 mm	HB	--	
3.00 mm	HB	--	
Injection	Dry	Unit	
Drying Temperature	80.0		°C
Drying Time	2.0 to 4.0		hr
Suggested Max Moisture	0.080		%
Rear Temperature	245 to 275		°C
Middle Temperature	260 to 285		°C
Front Temperature	270 to 295		°C
Nozzle Temperature	270 to 295		°C
Processing (Melt) Temp	270 to 295		°C
Mold Temperature	80.0 to 95.0		°C
Injection Pressure	3.50 to 12.5		MPa
Injection Rate	Fast		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT