

K-Prene GLC 6040

Thermoplastic Elastomer

Technovinyl Polymers India Ltd.

Message:

K-Prene GLC 6040 is a Thermoplastic Elastomer (TPE) material. It is available in Africa & Middle East.

Important attributes of K-Prene GLC 6040 are:

Chemical Resistant

Good UV Resistance

Heat Resistant

Sunlight Resistant

General Information			
Features	Acid Resistant		
	Alkali Resistant		
	Good Chemical Resistance		
	Good UV Resistance		
	High Heat Resistance		
	Low Compression Set		
	Ozone Resistant		
	Sunlight Resistant		
Uses	Rubber Replacement		
Appearance	Natural Color		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.920 to 0.960	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	35 to 45		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	2.45 to 3.43	MPa	ASTM D412
Tensile Elongation (Break)	> 700	%	ASTM D412
Compression Set			ASTM D395
40°C	36	%	
70°C	42	%	
125°C	52	%	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

