Fainplast PVC FKA 88/1

Polyvinyl Chloride

Fainplast Compounds S.r.l

Message:

Fainplast PVC FKA 88/1 is a Polyvinyl Chloride product. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Typical application: Wire & Cable.

Characteristics include:

Flame Retardant

Low Temperature Resistant

| General Information | | | |
|---------------------------|---------------------------|---------|---------------|
| Additive | Flame Retardant | | |
| Features | Flame Retardant | | |
| | Low Temperature Resistant | | |
| | | | |
| Uses | Insulation | | |
| | Wire & Cable Applications | | |
| | | | |
| Wire Types | R2 | | |
| Agency Ratings | CEI 20-22 | | |
| | EN 50363-3 | | |
| | | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 1.38 to 1.42 | g/cm³ | ISO 1183 |
| Hardness | Nominal Value | Unit | Test Method |
| Shore Hardness (Shore A) | 86 to 90 | | ISO 868 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Stress (Break) | > 18.0 | МРа | ISO 527-2 |
| Tensile Strain (Break) | > 280 | % | ISO 527-2 |
| Thermal | Nominal Value | Unit | Test Method |
| Cold Flexibility | -35 to -31 | °C | ISO 458/2 |
| Thermal Stability | > 1 | hr | CEI 20-34/3-2 |
| Electrical | Nominal Value | Unit | Test Method |
| Volume Resistivity (23°C) | 1.0E+14 | ohms·cm | ASTM D257 |
| Flammability | Nominal Value | Unit | Test Method |
| Oxygen Index | 28 to 30 | % | ISO 4589-2 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

