

FRIANYL® B3 VNGF25 V0

Polyamide 6

Nilit Plastics

Message:

FRIANYL® B3 VNGF25 V0 is a cross linkable Polyamide 6 (Nylon 6) compound, 25% glass fiber reinforced, flame retardant halogen and red phosphorous free and, UL listed V0.

This compound is intended for injection molding.

FRIANYL® B3 VNGF25 V0 is primarily designed for Electrical and Electronic industry. It is also suitable for Automotive applications.

General Information			
UL YellowCard	E172252-100760334	E331274-100305902	E86034-251975
	E172252-101977619		
Filler / Reinforcement	Glass Fiber,25% Filler by Weight		
Additive	Flame Retardant		
Features	Crosslinkable		
	Flame Retardant		
	Halogen Free		
	Low (to None) Phosphorus Content		
Uses	Automotive Applications		
	Electrical/Electronic Applications		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.38	g/cm³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow : 23°C	0.80	%	
Flow : 23°C	0.30	%	
Water Absorption			ISO 62
23°C, 24 hr	1.4	%	
Saturation, 23°C	4.5	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	9000	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	135	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	3.0	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	6.5	kJ/m²	
23°C	8.0	kJ/m²	
Charpy Unnotched Impact Strength			ISO 179/1eU
23°C	No Break		

30°C	45	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	> 250	°C	ISO 75-2/B
1.8 MPa, Unannealed	> 250	°C	ISO 75-2/A
Continuous Use Temperature ¹	125	°C	IEC 60216
Ball Pressure Test			IEC 60695-10-2
125°C	Pass		
165°C	Pass		
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity ²	1.0E+13	ohms	IEC 60093
Volume Resistivity (23°C)	1.0E+15	ohms·cm	IEC 60093
Electric Strength (2.00 mm)	18	kV/mm	IEC 60243-1
Comparative Tracking Index (3.20 mm, Solution A)	600	V	IEC 60112
Needle Flame Test			IEC 60695-11-5
1.00 mm	Pass		
2.00 mm	Pass		
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.400 mm	V-0		
0.800 mm	V-0		
1.60 mm	V-0		
3.20 mm	V-0		
Glow Wire Flammability Index			IEC 60695-2-12
0.800 mm	960	°C	
3.20 mm	960	°C	
Oxygen Index	32	%	ISO 4589-2
Flammability ³	SE		FMVSS 302
NOTE			
1.	20000 hr		
2.	23°C		
3.	355x100x1mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

