

Celcon® MC270

Acetal (POM) Copolymer

Celanese Corporation

Message:

Celcon® MC270 is a mineral coupled acetal copolymer designed for applications requiring improved stiffness, lower mold shrinkage and reduced warpage while maintaining the mechanical performance characteristics of an unfilled Celcon® M270 grade.

General Information			
UL YellowCard	E38860-239314		
Filler / Reinforcement	Mineral filler		
Features	Low warpage		
	Rigid, good		
	High liquidity		
	Low shrinkage		
RoHS Compliance	Contact manufacturer		
Multi-Point Data	Isothermal Stress vs. Strain (ISO 11403-1)		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.48	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow	1.9	%	ASTM D955
Transverse flow	1.6	%	ASTM D955
Vertical flow direction	1.6	%	ISO 294-4
Flow direction	1.9	%	ISO 294-4
Water Absorption			
Saturated, 23°C	0.75	%	ISO 62
Equilibrium, 23°C, 50% RH	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3150	MPa	ISO 527-2/1A/1
Tensile Strength			
Yield, 23°C	53.1	MPa	ASTM D638
Yield	57.0	MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	7.0	%	ISO 527-2/1A/50
Flexural Modulus (23°C)	3100	MPa	ISO 178
Flexural Stress (23°C)	77.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			
-30°C	4.5	kJ/m ²	ISO 179/1eA
23°C	5.4	kJ/m ²	ISO 179/1eA
Notched Izod Impact (23°C)	5.5	kJ/m ²	ISO 180/1A

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, not annealed	93.3	°C	ASTM D648
1.8 MPa, not annealed	101	°C	ISO 75-2/A
Melting Temperature ¹	165	°C	ISO 11357-3, ASTM D3418
Linear thermal expansion coefficient			ISO 11359-2
Flow	1.0E-4	cm/cm/°C	ISO 11359-2
Lateral	1.2E-4	cm/cm/°C	ISO 11359-2
Injection	Nominal Value	Unit	
Drying Temperature	80.0 - 100	°C	
Drying Time	3.0	hr	
Rear Temperature	170 - 180	°C	
Middle Temperature	180 - 190	°C	
Front Temperature	180 - 190	°C	
Nozzle Temperature	190 - 200	°C	
Processing (Melt) Temp	180 - 200	°C	
Mold Temperature	80.0 - 120	°C	
Injection Pressure	60.0 - 120	MPa	
Injection Rate	Slow		
Holding Pressure	60.0 - 120	MPa	
Back Pressure	0.00 - 0.500	MPa	
Injection instructions			
Manifold Temperature: 190 to 200°C Zone 4 Temperature: 190 to 200°C			
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT