Silopren® LSR 2671

Silicone Rubber, LSR

Momentive Performance Materials Inc.

Message:

Silopren LSR 2671 TP 3733 is a two-component liquid silicone rubber for injection moulding processes. Silopren LSR 2671 TP 3733 shows in comparison to Silopren LSR 2670 as non post-cure grade (NPC grade) a lower compression set after vulcanisation.

Key Features and Benefits

Vulcanisates consisting of Silopren LSR 2671 TP 3733 are distinguished by the following properties:

non post-cure

high reactivity

excellent thermal stability

high stability and flexibility at low temperatures

good rubber-like properties, high tear resistance

long service life at dynamic stress

high stability to ozone and ultraviolet light

outstanding resistance to ageing,

excellent dielectric behaviour over a wide range of temperatures,

not readily combustible, does not melt or drip

easy pigmentable with the LSR Colour Pastes

Potential Applications

Because of the outstanding properties Silopren LSR 2671 TP 3733 is particularly suitable for the following elastomeric articles: sealing elements, O-rings, stoppers, diaphragms, keypads, bellows, vibration dampers, switch cover, spark plug boots, cable connectors s.o.

General Information					
Features	Good Colorability				
	Good Stability				
	Good Tear Strength				
	Good Thermal Stability				
	Good UV Resistance				
	High Reactivity				
	Low Temperature Flexibility				
	Ozone Resistant				
	Vibration Damping				
Uses	Connectors				
	Diaphragms				
	Seals				
Forms	Liquid				
Processing Method	Injection Molding				
Physical	Nominal Value	Unit	Test Method		
Density	1.13	g/cm³	DIN 53479		
Hardness	Nominal Value	Unit	Test Method		
Durometer Hardness (Shore A)	65		DIN 53505		
Elastomers	Nominal Value	Unit	Test Method		
Tensile Strength	9.00	MPa	DIN 53504		

Tensile Elongation (Break)	450	%	DIN 53504
Tear Strength ¹	45.0	kN/m	ASTM D624
Compression Set (175°C, 22 hr)	25	%	DIN 53517
Thermoset	Nominal Value	Unit	Test Method
Thermoset Components			
Part A	Mix Ratio by Weight: 1.0		
Part B	Mix Ratio by Weight: 1.0		
Additional Information	Nominal Value	Unit	Test Method
Vulcanization (175°C)	10.0	min	
Uncured Properties	Nominal Value	Unit	Test Method
Color			
2	Translucent		
3	Translucent		
Viscosity			DIN 53018
20°C ⁴	550	Pa·s	
20°C ⁵	550	Pa·s	
Pot Life (20°C)	4300	min	
NOTE			
1.	Die B		
2.	Part B		
3.	Part A		
4.	Part B		
5.	Part A		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

