

# TATREN® RM 60 57

Polypropylene Random Copolymer

Slovnaft Petrochemicals, s.r.o.

## Message:

TATREN RM 60 57 is a controlled rheology random copolymer of excellent processing stability and high fluidity. It contains unique and very effective clarifying agent and antistatic agent.

TATREN RM 60 57 is characterised by good transparency, high gloss and good organoleptic properties.

### Applications

TATREN RM 60 57 is intended for thin wall injection moulding of products where good clarity and low haze is required - video and DVD boxes, food packages, cups, closures, household articles etc. Thanks to used additive package it can be processed at significantly lower temperatures and gives potential for cycle time reduction.

TATREN RM 60 57 is suitable for food contact. The product complies with Food Contact Regulations.

General Information			
Additive	Antistatic		
	Clarifier		
Features	Food Contact Acceptable		
	Good Organoleptic Properties		
	Good Processing Stability		
	High Clarity		
	High Gloss		
	Random Copolymer		
Uses	Closures		
	Containers		
	Cups		
	Food Packaging		
	Household Goods		
Appearance	Clear/Transparent		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	60	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	90		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (Injection Molded)	1200	MPa	ISO 527-2
Tensile Stress (Yield, Injection Molded)	29.0	MPa	ISO 527-2
Tensile Strain (Yield, Injection Molded)	11	%	ISO 527-2
Flexural Modulus (Injection Molded)	1100	MPa	ISO 178

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C, Injection Molded)	4.0	kJ/m <sup>2</sup>	ISO 180/A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	80.0	°C	ISO 75-2/B
Optical	Nominal Value	Unit	Test Method
Haze	11	%	ISO 14782
Injection	Nominal Value	Unit	
Processing (Melt) Temp	190 to 230	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

