

TRIMID® N6-200L

Polyamide 6

Polymer Technology and Services, LLC

Message:

TRIMID® N6-200L is a Polyamide 6 (Nylon 6) product. It can be processed by injection molding and is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Primary characteristic: lubricated.

General Information			
Additive	Lubricant		
Features	Lubricated		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.14	g/cm ³	ASTM D792
Water Absorption (24 hr)	1.6	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	85.5	MPa	ASTM D638
Tensile Elongation (Break)	100	%	ASTM D638
Flexural Modulus	2830	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.17 mm)	64	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	174	°C	
1.8 MPa, Unannealed	63.0	°C	
Melting Temperature	216	°C	
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	3.0 to 4.0	hr	
Rear Temperature	< 216	°C	
Middle Temperature	227 to 254	°C	
Front Temperature	238 to 266	°C	
Nozzle Temperature	238 to 266	°C	
Processing (Melt) Temp	232 to 271	°C	
Mold Temperature	21.1 to 93.3	°C	
Injection Pressure	82.7 to 172	MPa	
Back Pressure	0.00 to 0.345	MPa	
Screw Speed	40 to 80	rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT