POLYPRO® 5030

Polypropylene Homopolymer

YUHWA Korea Petrochemical Ind. Co., Ltd.

Message:

 ${\tt POLYPRO} @~5030~is~a~Polypropylene~Homopolymer~(PP~Homopolymer)~material.~It~is~available~in~Asia~Pacific.}\\$

Important attributes of POLYPRO® 5030 are:

RoHS Compliant

High Flow

Homopolymer

Typical applications include:

Fabrics/Fibers

Food Contact Applications

Nonwovens

General Information			
Features	High Flow		
	Homopolymer		
Uses	Fabrics		
	Fibers		
	Nonwovens		
Agency Ratings	FDA Food Contact, Unspecified Rating		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16			
kg)	40	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.0 to 2.0	%	Internal Method
Water Absorption (Equilibrium)	< 0.010	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	98		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	30.4	MPa	ASTM D638
Tensile Elongation (Break)	> 500	%	ASTM D638
Flexural Modulus	1370	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	39	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8			
MPa, Unannealed)	105	°C	ASTM D648
Vicat Softening Temperature	150	°C	ASTM D1525

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

ASTM D3418

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

