

# IPC PP 4840H-T

Polypropylene Homopolymer

International Polymers Corporation

## Message:

IPC PP 4840H-T is a Polypropylene Homopolymer (PP Homopolymer) material filled with 40% talc. It is available in North America. Primary attribute of IPC PP 4840H-T: Homopolymer.

Typical application of IPC PP 4840H-T: Automotive

General Information			
Filler / Reinforcement	Talc,40% Filler by Weight		
Features	Homopolymer		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.24	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.80 to 1.2	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	33.8	MPa	ASTM D638
Flexural Modulus	3100	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	32	J/m	ASTM D256A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT