

Sumitomo PP AW564

Polypropylene Copolymer
Sumitomo Chemical Asia

Message:

Applications For industrial applications such as crates, washing machine parts, electrical appliances, household appliances, etc.
Characteristics Medium high flow, high impact, high stiffness, and high heat stability.

General Information			
Features	Block Copolymer		
	High Flow		
	High Heat Resistance		
	High Impact Resistance		
	High Stiffness		
Uses	Appliance Components		
	Appliances		
	Crates		
Agency Ratings	FDA 21 CFR 177.1520(c) 3.1a		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.900	g/cm ³	ASTM D792A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	9.0	g/10 min	ASTM D1238
Molding Shrinkage			Internal Method
Across Flow	1.6	%	
Flow	1.4	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness	96		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	28.0	MPa	
Break	15.0	MPa	
Flexural Modulus	1530	MPa	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ASTM D256
-20°C	5.0	kJ/m ²	
23°C	10	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load (0.45 MPa, Unannealed)	124	°C	ASTM D648
Vicat Softening Temperature	153	°C	ASTM D1525 ¹
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Processing (Melt) Temp	190 to 230	°C	
Mold Temperature	20.0 to 70.0	°C	
NOTE			

1. Loading 1 (10 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

