

Infino CF-3200HF

Polycarbonate
SAMSUNG SDI CO., LTD.

Message:

Infino CF-3200HF is a Polycarbonate (PC) product filled with glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.
Characteristics include:
Flame Rated
RoHS Compliant

General Information			
UL YellowCard	E115797-640431		
Filler / Reinforcement	Glass Fiber		
RoHS Compliance	RoHS Compliant		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.33	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (250°C/10.0 kg)	23	g/10 min	ASTM D1238, ISO 1133
Molding Shrinkage			
Flow : 3.20 mm	0.30 to 0.50	%	ASTM D955, ISO 2577
Across Flow : 3.20 mm	0.30 to 0.50	%	ASTM D955
Water Absorption			
23°C, 24 hr	0.30	%	ASTM D570
Equilibrium, 23°C, 50% RH	0.30	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	116		ASTM D785, ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			
Yield ¹	98.0	MPa	ASTM D638
Yield	100	MPa	ISO 527-2/5
Flexural Modulus			
-- ²	5500	MPa	ASTM D790
-- ³	6000	MPa	ISO 178
Flexural Strength			
-- ⁴	140	MPa	ASTM D790
-- ⁵	170	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁶ (23°C)	25	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
23°C, 3.18 mm	190	J/m	ASTM D256
23°C ⁷	19	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load (1.8 MPa, Unannealed, 6.40 mm)	141	°C	ASTM D648
Vicat Softening Temperature	137	°C	ISO 306/B50
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
0.800 mm	V-2		
3.20 mm	V-1		
Injection	Nominal Value	Unit	
Drying Temperature			
--	100	°C	
Desiccant Dryer	100	°C	
Drying Time			
--	4.0 to 6.0	hr	
Desiccant Dryer	2.0 to 4.0	hr	
Suggested Max Moisture	< 0.050	%	
Rear Temperature	270	°C	
Middle Temperature	280 to 290	°C	
Front Temperature	300	°C	
Nozzle Temperature	300	°C	
Mold Temperature	80.0 to 120	°C	
Injection Pressure	98.1	MPa	
Back Pressure	0.490 to 1.96	MPa	
Screw Speed	50 to 150	rpm	
NOTE			
1.	5.0 mm/min		
2.	2.8 mm/min		
3.	2.0 mm/min		
4.	2.8 mm/min		
5.	2.0 mm/min		
6.	Thickness: 4 mm		
7.	Thickness: 4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT