

KOPLA PA6 KNG1050

Polyamide 6

KOPLA Co., Ltd.

Message:

KOPLA PA6 KNG1050 is a Polyamide 6 (Nylon 6) material filled with glass fiber. It is available in Asia Pacific. Primary attribute of KOPLA PA6 KNG1050: Flame Rated.
Typical application of KOPLA PA6 KNG1050: Automotive

General Information			
Filler / Reinforcement	Glass Fiber		
Uses	Automotive Exterior Parts		
	Automotive Interior Parts		
	Automotive Under the Hood		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.56	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.10 to 0.60	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.90	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	122		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	216	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	1.5	%	ASTM D638
Flexural Modulus (23°C)	12500	MPa	ASTM D790
Flexural Strength (23°C)	294	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	220	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	220	°C	
1.8 MPa, Unannealed	216	°C	
Melting Temperature	220	°C	
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength	25	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

