

# Buna® EP T 3950

Ethylene Propylene Diene Terpolymer

LANXESS Corporation

## Message:

Ethylene-propylene-diene rubber (EPDM), with ethylidene norbornene (ENB) as diene; amorphous; low viscosity, fast cure rate.

General Information			
Features	Low viscosity		
	Fast curing		
	amorphous		
Forms	bag		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.858	g/cm <sup>3</sup>	ASTM D792
Mooney Viscosity (ML 1+8, 100°C)	48 - 60	MU	ASTM D1646
Ethylene Content	52.0 - 60.0	wt%	ASTM D3900
Ethylidene Norbornene (ENB) Content	10.0 - 12.8	wt%	ASTM D6047
Additional Information			

Total Ash, ISO 247/ASTM D5667: <0.5%Stabilizer: Non-stainingVolatile Matter, ISO 248/ASTM D5668: <0.75 wt%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

