

WPP PP PPH3TF2-Natural

Polypropylene Homopolymer
Washington Penn Plastic Co. Inc.

Message:

Properties shown below for this filled blend are typical for a 20% talc-reinforced polypropylene homopolymer. This basic product satisfies many application needs. Special compounds are available.

General Information			
Filler / Reinforcement	Talc filler, 20% filler by weight		
Features	Homopolymer		
	High liquidity		
	Heat resistance, high		
Uses	Application in Automobile Field		
	Car interior equipment		
Appearance	Available colors		
	Natural color		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.03	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	6.0	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	34.0	MPa	ASTM D638
Flexural Modulus ²	2300	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	26	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	74.0	°C	ASTM D648
Additional Information			
Tested at 23 ± 2°C (73.4 ± 3.6°F) and 50 ± 5% relative humidity unless otherwise noted.			
Injection	Nominal Value	Unit	
Drying Temperature	71.1 - 87.8	°C	
Drying Time	1.0	hr	
Rear Temperature	221 - 227	°C	
Middle Temperature	221 - 227	°C	
Front Temperature	224 - 229	°C	
Nozzle Temperature	229 - 241	°C	

Mold Temperature	15.6 - 48.9	°C
Injection Pressure	4.14 - 7.58	MPa
Holding Pressure	1.72 - 4.83	MPa
Back Pressure	0.689 - 1.38	MPa
Clamp Tonnage	3.4 - 5.5	kN/cm ²
Cushion	3.18 - 6.35	mm

Injection instructions

Injection Speed: 1.5 to 2.5 in/s Zone 4 Temperature: 445 to 455°F Hot Runner Temperature: 445 to 475°F Hydraulic Oil Temperature: 110 to 125°F Shot Capacity vs. Barrel Capacity: 2.5 to 4 Screw Decompression: 0.1 to 0.25 in

NOTE

1. 50 mm/min
2. 1.3 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

