SQUARE® LIM1500-70A/B

Silicone Rubber, LSR

Shenzhen SQUARE Silicone Co., Ltd.

Message:

Liquid silicone rubber material for indoor medium and high voltage resistance terminal

Product Description

2-part liquid silicone rubber, which is suitable for injection or extrusion molding with tracking resistance 1A 3.5 grade, mixing ration of parts A:B=1:1, with standing middle and high voltage, catalyzed by platinum. The appearance of A is transparent and B is grey.

Key Features

Injection molding

High tear strength

High elongation

Low tension set

LOW TELISION SET

Rapid vulcanization Excellent electric performance

At the temperature of 20 and in the condition of air-proof, the shelf life is 5 days after mixing A and B, the shelf life will decrease with the increasing of the temperature.

Applications

General Information

Medium and high voltage resistant cable accessories, indoor cold shrink and terminal, tie-in and jacket etc suitable for injection and extrusion molding

General Information					
Features	Fast curing				
	Good electrical performance				
	Good tear strength				
	Track Resistance				
	Extended tensile rate				
Uses	Cable sheath				
	Electrical/Electronic Applications				
	Wire and cable applications				
Processing Method	Extrusion				
	Liquid Injection Molding (LIM)				
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	1.18	g/cm³	ASTM D792		
Hardness	Nominal Value	Unit	Test Method		
Durometer Hardness (Shore A)	70		ASTM D2240		
Elastomers	Nominal Value	Unit	Test Method		
Tensile Strength	7.10	МРа	ASTM D412		
Tensile Elongation (Break)	340	%	ASTM D412		
Tear Strength ¹	30.0	kN/m	ASTM D624		
Thermoset	Nominal Value	Unit			
Thermoset Components					
Component a	Mixing ratio by weight: 1.0	Mixing ratio by weight: 1.0			

Component B	Mixing ratio by weight: 1.0	Mixing ratio by weight: 1.0		
Pot Life (20°C)	7200	min		
Shelf Life	52	wk		
Post Cure Time (200°C)	4.0	hr		
Uncured Properties	Nominal Value	Unit		
Color				
2	Clear/Transparent			
3	Grey			
Solids Content	100	%		
Viscosity	1200	Pa·s		
Curing Time (140°C)	0.17	hr		
NOTE				
1.	B mould			
2.	Part A			
3.	Part B			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

