

MAJORIS DE265 - 7905/3

Polypropylene

AD majoris

Message:

DE265 - 7905/3 is a 25% mineral filled polypropylene elastomer modified compound intended for injection moulding.

DE265 - 7905/3 has been developed especially for the automotive interior parts, requiring good impact strength/stiffness, very good scratch resistance and UV resistance.

The product is available in natural (DE265) and black (DE265-8229) but other colours can be provided on request.

APPLICATIONS

Automotive interior parts

General Information			
Filler / Reinforcement	Mineral filler, 25% filler by weight		
Additive	Impact modifier		
Features	Impact modification		
	Rigid, good		
	Impact resistance, good		
	Good UV resistance		
	Recyclable materials		
	Scratch resistance		
Uses	Car interior parts		
Appearance	Black		
	Available colors		
	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.10	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	7.0	g/10 min	ISO 1133
Molding Shrinkage	0.80 - 1.1	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1900	MPa	ISO 527-2/1
Tensile Stress (Yield)	20.0	MPa	ISO 527-2/50
Flexural Modulus ¹	2100	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1A
0°C	5.5	kJ/m ²	ISO 179/1A
23°C	15	kJ/m ²	ISO 179/1A
Thermal	Nominal Value	Unit	Test Method

Heat Deflection Temperature			
0.45 MPa, not annealed	110	°C	ISO 75-2/B
1.8 MPa, not annealed	60.0	°C	ISO 75-2/A
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	220 - 260	°C	
Mold Temperature	30.0 - 50.0	°C	
Injection Rate	Moderate		
Injection instructions			
Holding pressure: 50 to 70% of the injection pressure			
NOTE			
1.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT