

Durethan® AKV 30 000000

Polyamide 66

LANXESS GmbH

Message:

PA 66, 30 % glass fibers, injection molding

General Information				
UL YellowCard		E245249-473556		
Filler / Reinforcement		Glass fiber reinforced material, 30% filler by weight		
Agency Ratings		EC 1907/2006 (REACH)		
Forms		Particle		
Processing Method		Injection molding		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.36	--	g/cm ³	ISO 1183
Apparent Density	0.70	--	g/cm ³	ISO 60
Molding Shrinkage				ISO 2577
Vertical flow direction: 280°C, 3.00mm ¹	1.5	--	%	ISO 2577
Vertical flow direction: 120°C, 4 hours, 3.00mm ²	0.050	--	%	ISO 2577
Flow direction: 280°C, 3.00mm ³	0.35	--	%	ISO 2577
Flow direction: 120°C, 4 hours, 3.00mm ⁴	0.040	--	%	ISO 2577
Water Absorption				ISO 62
Saturated, 23°C	5.5	--	%	ISO 62
Equilibrium, 23°C, 50% RH	2.0	--	%	ISO 62
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness	230	130	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus				
23°C	10300	6790	MPa	ASTM D638
23°C	10600	7000	MPa	ISO 527-2/1
Tensile Strength				
Fracture, 23°C	179	121	MPa	ASTM D638
Fracture, 23°C	185	125	MPa	ISO 527-2/5
Tensile Elongation (Break, 23°C)	3.0	6.0	%	ASTM D638, ISO 527-2/5
Flexural Modulus				
23°C	841	590	MPa	ASTM D790
23°C ⁵	8400	5900	MPa	ISO 178/A

Flexural Strength				
23°C	290	200	MPa	ASTM D790
3.5% strain, 23°C	--	165	MPa	ISO 178/A
23°C ⁶	290	200	MPa	ISO 178/A
Flexural Strain at Flexural Strength ⁷ (23°C)	4.0	6.0	%	ISO 178/A
ISO Shortname	PA 66, GR, 14-110, GF30	--		ISO 1874
Residual Moisture Content	0.030 - 0.12		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	10	10	kJ/m ²	ISO 179/1eA
23°C	10	15	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	70	70	kJ/m ²	ISO 179/1eU
23°C	90	90	kJ/m ²	ISO 179/1eU
Notched Izod Impact				ISO 180/1A
-40°C	< 10	< 10	kJ/m ²	ISO 180/1A
-30°C	< 10	< 10	kJ/m ²	ISO 180/1A
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, not annealed	250	--	°C	ISO 75-2/B
1.8 MPa, not annealed	250	--	°C	ISO 75-2/A
8.0 MPa, not annealed	135	--	°C	ISO 75-2/C
Vicat Softening Temperature	> 230	--	°C	ISO 306/B120
Melting Temperature ⁸	263	--	°C	ISO 11357-3
Linear thermal expansion coefficient				ISO 11359-2
Flow: 23 to 55°C	2.5E-5	--	cm/cm/°C	ISO 11359-2
Lateral: 23 to 55°C	1.0E-4	--	cm/cm/°C	ISO 11359-2
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+14	1.0E+13	ohms	IEC 60093
Volume Resistivity (23°C)	1.0E+15	1.0E+12	ohms·cm	IEC 60093
Dielectric Strength (23°C, 1.00 mm)	40	35	kV/mm	IEC 60243-1
Relative Permittivity				IEC 60250
23°C, 100 Hz	4.00	10.0		IEC 60250
23°C, 1 MHz	4.00	4.00		IEC 60250
Dissipation Factor				IEC 60250
23°C, 100 Hz	9.0E-3	0.27		IEC 60250
23°C, 1 MHz	0.018	0.080		IEC 60250

Comparative Tracking Index (Solution A)	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
1.60 mm	HB	--		UL 94
3.20 mm	HB	--		UL 94
Glow Wire Flammability Index (2.00 mm)	600	--	°C	IEC 60695-2-12
Oxygen Index ⁹	23	--	%	ISO 4589-2
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 - 6.0		hr	
Processing (Melt) Temp	280 - 300		°C	
Mold Temperature	80.0 - 120		°C	

NOTE

- 150x105x3mm, 80°C MT, 400 bar
- 150x105x3mm
- 150x105x3mm, 80°C MT, 400 bar
- 150x105x3mm
- 2.0 mm/min
- 2.0 mm/min
- 2 mm/min
- 10°C/min
- Procedure A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT