

Durethan® B 40 SK 000000

Polyamide 6

LANXESS Corporation

Message:

PA 6, non-reinforced, injection molding

General Information				
UL YellowCard		E245249-473565		
Agency Ratings		EC 1907/2006 (REACH)		
Forms		Particle		
Processing Method		Injection molding		
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity				
--	1.14	--	g/cm ³	ASTM D792
23°C	1.14	--	g/cm ³	ISO 1183
Apparent Density	0.70	--	g/cm ³	ISO 60
Molding Shrinkage				ISO 2577
Vertical flow direction: 280°C, 3.00mm ¹	0.96	--	%	ISO 2577
Vertical flow direction: 120°C, 4 hours, 3.00mm ²	0.20	--	%	ISO 2577
Flow direction: 280°C, 3.00mm ³	0.90	--	%	ISO 2577
Flow direction: 120°C, 4 hours, 3.00mm ⁴	0.21	--	%	ISO 2577
Water Absorption				ISO 62
Saturated, 23°C	10	--	%	ISO 62
Equilibrium, 23°C, 50% RH	3.0	--	%	ISO 62
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness	150	50.0	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus				
23°C ⁵	3100	1000	MPa	ASTM D638
23°C	3200	900	MPa	ISO 527-2/1
Tensile Strength				
Yield, 23°C	84.8	40.0	MPa	ASTM D638
Yield, 23°C	85.0	40.0	MPa	ISO 527-2/50
Fracture, 23°C	55.2	55.2	MPa	ASTM D638
Tensile Elongation				
Yield, 23°C	4.0	25	%	ASTM D638, ISO 527-2/50
Fracture, 23°C	> 50	> 50	%	ASTM D638

Nominal Tensile Strain at Break (23°C)	20	> 50	%	ISO 527-2/50
Tensile Creep Modulus				ISO 899-1
1 hr	--	700	MPa	ISO 899-1
1000 hr	--	570	MPa	ISO 899-1
Flexural Modulus				
23°C	2700	703	MPa	ASTM D790
23°C ⁶	2800	800	MPa	ISO 178/A
Flexural Strength				
5.0% strain, 23°C	115	35.0	MPa	ASTM D790
3.5% strain, 23°C	95.0	25.0	MPa	ISO 178/A
23°C ⁷	115	35.0	MPa	ISO 178/A
Flexural Strain at Flexural Strength ⁸ (23°C)	6.0	9.0	%	ISO 178/A
Burning Behavior ⁹ (> 1.00 mm)	passed	--		ISO 3795
ISO Shortname	PA 6, GR, 22-030	--		ISO 1874
Residual Moisture Content	0.030 - 0.12		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-40°C	< 10	< 10	kJ/m ²	ISO 179/1eA
-30°C	< 10	< 10	kJ/m ²	ISO 179/1eA
23°C	< 10	50	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	No Break	No Break		ISO 179/1eU
23°C	No Break	No Break		ISO 179/1eU
Notched Izod Impact				
23°C, 3.18 mm	69	960	J/m	ASTM D256
-40°C	< 10	< 10	kJ/m ²	ISO 180/1A
-30°C	< 10	< 10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength				ISO 180/1U
-30°C	No Break	No Break		ISO 180/1U
23°C	No Break	No Break		ISO 180/1U
Multi-Axial Instrumented Impact Energy				ISO 6603-2
-30°C	160	--	J	ISO 6603-2
23°C	160	165	J	ISO 6603-2
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				
0.45 MPa, unannealed, 39.9mm	180	--	°C	ASTM D648

0.45 MPa, not annealed	150	--	°C	ISO 75-2/B
1.8 MPa, not annealed	55.0	--	°C	ISO 75-2/A
1.8 MPa, annealing, 3.99mm	60.0	--	°C	ASTM D648
8.0 MPa, not annealed	45.0	--	°C	ISO 75-2/C
Vicat Softening Temperature	200	--	°C	ISO 306/B50, ISO 306/B120
Melting Temperature ¹⁰	222	--	°C	ISO 11357-3
Linear thermal expansion coefficient				ISO 11359-2
Flow: 23 to 55°C	8.0E-5	--	cm/cm/°C	ISO 11359-2
Lateral: 23 to 55°C	9.0E-5	--	cm/cm/°C	ISO 11359-2
RTI Elec (1.50 mm)	105	--	°C	UL 746
RTI Imp (1.50 mm)	65.0	--	°C	UL 746
RTI (1.50 mm)	75.0	--	°C	UL 746
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+13 - 1.0E+14	1.0E+12 - 1.0E+13	ohms	IEC 60093
Volume Resistivity (23°C)	1.0E+15	1.0E+11 - 1.0E+12	ohms·cm	IEC 60093
Dielectric Strength				IEC 60243-1
23°C, 1.00 mm	30	35	kV/mm	IEC 60243-1
23°C, 3.00 mm	30	35	kV/mm	IEC 60243-1
Dielectric Constant				IEC 60250
23°C, 50 Hz ¹¹	3.80	16.0		IEC 60250
23°C, 1 MHz ¹²	3.40	4.70		IEC 60250
23°C, 100 Hz	4.00	20.0		IEC 60250
23°C, 1 MHz	3.50	4.50		IEC 60250
Dissipation Factor				IEC 60250
23°C, 50 Hz	0.050	2.8		IEC 60250
23°C, 100 Hz	0.012	0.19		IEC 60250
	0.060	0.40		
23°C, 1 MHz	0.020	0.14		IEC 60250
Comparative Tracking Index				
Solution a	600	--	V	IEC 60112
Solution B	600	--	V	IEC 60112
--	--	600	V	ASTM D3638
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.800 mm	HB	--		UL 94
1.50 mm	HB	--		UL 94
1.60 mm	HB	--		UL 94
3.00 mm	HB	--		UL 94

Glow Wire Flammability Index (2.00 mm)	750	--	°C	IEC 60695-2-12
Oxygen Index ¹³	24	--	%	ISO 4589-2
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 - 6.0		hr	
Processing (Melt) Temp	260 - 280		°C	
Mold Temperature	80.0 - 100		°C	

NOTE

1.	150x105x3mm, 80°C MT, 500 bar
2.	150x105x3mm
3.	150x105x3mm, 80°C MT, 500 bar
4.	150x105x3mm
5.	1.0 mm/min
6.	2.0 mm/min
7.	2.0 mm/min
8.	2 mm/min
9.	US-FMVSS302
10.	10°C/min
11.	Tinfoil Electrodes
12.	Tinfoil Electrodes
13.	Procedure A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT