

Tecotek® PC30 NL RX

Polycarbonate
Eurotec Engineering Plastics

Message:
PC, unfilled, improved flow & low temperature impact, natural

General Information			
Features	Good Flow		
	Low Temperature Impact Resistance		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Appearance	Natural Color		
Processing Method	Injection Molding		
Resin ID (ISO 1043)	PC		
Physical	Nominal Value	Unit	Test Method
Density	1.19	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	20	g/10 min	ISO 1133
Molding Shrinkage			Internal Method
Across Flow	0.60	%	
Flow	0.60	%	
Water Absorption (Equilibrium, 23°C, 50% RH)	0.20	%	ISO 62
Moisture Content	< 0.10	%	ISO 15512
Back Pressure	Low		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2250	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	65.0	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	> 50	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ISO 180/1A
-30°C	40	kJ/m²	
23°C	70	kJ/m²	
Unnotched Izod Impact Strength			ISO 180/1U
-30°C	No Break		
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	140	°C	ISO 75-2/B
1.8 MPa, Unannealed	125	°C	ISO 75-2/A

Vicat Softening Temperature	145	°C	ISO 306/B
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms·cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.750 mm	HB		
1.60 mm	HB		
Glow Wire Flammability Index (2.00 mm)	850	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (2.00 mm)	875	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	3.0 to 4.0	hr	
Hopper Temperature	60.0 to 80.0	°C	
Processing (Melt) Temp	260 to 300	°C	
Mold Temperature	80.0 to 100	°C	
Injection Rate	Moderate-Fast		
Holding Pressure	60.0 to 120	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

