

LNP™ LUBRILOY™ RF208 compound

Polyamide 66

SABIC Innovative Plastics

Message:

LNP LUBRILOY* RF208 is a compound based on Nylon 66 resin containing 40% Glass Fiber, Proprietary Lubricant. Added features of this material include: Wear Resistant.

Also known as: LNP* LUBRILOY* Compound RF-40

Product reorder name: RF208

General Information			
Filler / Reinforcement	Glass Fiber,40% Filler by Weight		
Additive	Lubricant		
Features	Good Wear Resistance		
	Lubricated		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.34	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow : 24 hr	0.40	%	ASTM D955
Across Flow : 24 hr	1.1	%	ASTM D955, ISO 294-4
Flow : 24 hr	0.41	%	ISO 294-4
Water Absorption			
24 hr, 50% RH	0.28	%	ASTM D570
Equilibrium, 23°C, 50% RH	0.40	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	12300	MPa	ASTM D638
--	10500	MPa	ISO 527-2/1
Tensile Strength			
Break	139	MPa	ASTM D638
Break	137	MPa	ISO 527-2
Tensile Elongation			
Break	2.5	%	ASTM D638
Break	2.7	%	ISO 527-2
Flexural Modulus			
--	9030	MPa	ASTM D790
--	11300	MPa	ISO 178
Flexural Strength			
--	200	MPa	ASTM D790
--	211	MPa	ISO 178

Coefficient of Friction			ASTM D3702 Modified
vs. Itself - Dynamic	0.41		
vs. Itself - Static	0.30		
Wear Factor - Washer	54.0	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D3702 Modified
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	130	J/m	ASTM D256
23°C ²	13	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	720	J/m	ASTM D4812
23°C ³	56	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	10.6	J	ASTM D3763
--	3.59	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed, 3.20 mm	242	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ⁴	238	°C	ISO 75-2/Af
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.15 to 0.25	%	
Rear Temperature	266 to 277	°C	
Middle Temperature	282 to 293	°C	
Front Temperature	293 to 304	°C	
Processing (Melt) Temp	271 to 282	°C	
Mold Temperature	82.2 to 93.3	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

