

ROPOTEN® T FV-03-223-2

Low Density Polyethylene

LUKOIL Bulgaria Ltd.

Message:

For production of bags for industrial purposes, for blow-moulded articles, etc.

General Information			
Additive	Antioxidant (1500 ppm) 1		
Features	Antioxidant		
Uses	Bags		
	Blow Molding Applications		
	Industrial Applications		
Appearance	Natural Color		
Forms	Pellets		
Processing Method	Blow Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.919 to 0.922	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.20 to 0.40	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	> 15.5	MPa	ASTM D638
Tensile Elongation (Break)	> 600	%	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	> 90.0	°C	ASTM D1525

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

