

KOPLA PA66 KDE1030

Polyamide 66

KOPLA Co., Ltd.

Message:

KOPLA PA66 KDE1030 is a Polyamide 66 (Nylon 66) material. It is available in Asia Pacific.

Important attributes of KOPLA PA66 KDE1030 are:

Flame Rated

Impact Modified

Typical applications include:

Automotive

Plumbing/Piping/Potable Water

Safety Equipment

General Information	
Additive	Impact Modifier
Features	Impact Modified
Uses	Automotive Exterior Parts
	Automotive Under the Hood
	Piping
	Safety Helmets

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.06	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	1.9 to 3.0	%	ASTM D955
Water Absorption (23°C, 24 hr)	1.2	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	105		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	49.0	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	90	%	ASTM D638
Flexural Modulus (23°C)	1470	MPa	ASTM D790
Flexural Strength (23°C)	62.8	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	No Break		ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	190	°C	ASTM D648
Melting Temperature	260	°C	
CLTE - Flow	7.5E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength	24	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

