

LNP™ VERTON™ NV0081EV_GY7E149

compound

Polycarbonate + ABS

SABIC Innovative Plastics

Message:

Preliminary data for 40% long fiber single pellet non-halogen FR color filled PC/ABS

General Information			
Filler / Reinforcement	Long Glass Fiber,40% Filler by Weight		
Features	Flame Retardant		
	Halogen Free		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.54	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			ASTM D955
Flow : 24 hr	0.060 to 0.26	%	
Across Flow : 24 hr	0.31 to 0.51	%	
Water Absorption			
24 hr	0.057	%	ASTM D570
23°C, 24 hr	0.075	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	12300	MPa	ASTM D638
--	10800	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	92.0	MPa	ASTM D638
Yield	100	MPa	ISO 527-2/5
Break ³	92.0	MPa	ASTM D638
Break	100	MPa	ISO 527-2/5
Tensile Elongation			
Yield ⁴	0.90	%	ASTM D638
Yield	0.90	%	ISO 527-2/5
Break ⁵	0.90	%	ASTM D638
Break	0.90	%	ISO 527-2/5
Flexural Modulus			
50.0 mm Span ⁶	12900	MPa	ASTM D790
-- ⁷	12400	MPa	ISO 178
Flexural Stress			

--	152	MPa	ISO 178
Yield, 50.0 mm Span ⁸	156	MPa	ASTM D790
Break, 50.0 mm Span ⁹	156	MPa	ASTM D790
Flexural Strain at Break ¹⁰	1.3	%	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
-40°C	300	J/m	ASTM D256
23°C	250	J/m	ASTM D256
-40°C ¹¹	29	kJ/m ²	ISO 180/1A
23°C ¹²	26	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
-40°C	480	J/m	ASTM D4812
23°C	440	J/m	ASTM D4812
-40°C ¹³	27	kJ/m ²	ISO 180/1U
23°C ¹⁴	32	kJ/m ²	ISO 180/1U
Instrumented Dart Impact (23°C, Total Energy)	11.5	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed, 3.20 mm	88.0	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ¹⁵	89.0	°C	ISO 75-2/Af
CLTE			ASTM E831
Flow : -40 to 40°C	2.2E-5	cm/cm/°C	
Transverse : -40 to 40°C	3.8E-5	cm/cm/°C	
Flammability	Nominal Value		Test Method
Flame Rating (1.55 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	30.0 to 40.0	°C	
Drying Time	2.0 to 4.0	hr	
Rear Temperature	205 to 235	°C	
Middle Temperature	210 to 245	°C	
Front Temperature	215 to 245	°C	
Processing (Melt) Temp	220 to 255	°C	
Mold Temperature	35.0 to 65.0	°C	
Back Pressure	0.150 to 0.300	MPa	
Screw Speed	12 to 40	rpm	
NOTE			
1.	50 mm/min		
2.	Type I, 5.0 mm/min		
3.	Type I, 5.0 mm/min		
4.	Type I, 5.0 mm/min		
5.	Type I, 5.0 mm/min		

6.	1.3 mm/min
7.	2.0 mm/min
8.	1.3 mm/min
9.	1.3 mm/min
10.	2 mm/min
11.	80*10*4
12.	80*10*4
13.	80*10*4
14.	80*10*4
15.	80*10*4 mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

