

LNP™ FARADEx™ MS003 compound

Polypropylene
SABIC Innovative Plastics

Message:

LNP* Faradex* MS003 is a compound based on Polypropylene resin containing Stainless Steel. Added features of this material include: Electrically Conductive, EMI/RFI Shielding.

Also known as: LNP* FARADEx* Compound MS-1003

Product reorder name: MS003

General Information			
Filler / Reinforcement	Stainless steel fiber		
Features	Conductivity		
	Electromagnetic shielding (EMI)		
	Radio frequency shielding (RFI)		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.01	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow: 24 hours	1.2	%	ASTM D955
Transverse flow: 24 hours	1.3	%	ASTM D955
Vertical flow direction: 24 hours	1.3	%	ISO 294-4
Flow direction: 24 hours	1.2	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	1200	MPa	ASTM D638
--	1300	MPa	ISO 527-2/1
Tensile Strength			
Yield	20.0	MPa	ASTM D638
Yield	21.0	MPa	ISO 527-2
Fracture	15.2	MPa	ASTM D638
Fracture	15.0	MPa	ISO 527-2
Tensile Elongation			
Yield	6.2	%	ASTM D638
Yield	5.2	%	ISO 527-2
Fracture	88	%	ASTM D638
Fracture	72	%	ISO 527-2
Flexural Modulus			
--	1190	MPa	ASTM D790
--	1500	MPa	ISO 178
Flexural Strength			

--	27.6	MPa	ASTM D790
--	32.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	270	J/m	ASTM D256
23°C ²	25	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	1200	J/m	ASTM D4812
23°C ³	80	kJ/m ²	ISO 180/1U
Multi-Axial Instrumented Impact Energy	22.0	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 3.20mm	92.2	°C	ASTM D648
0.45 MPa, unannealed, 64.0mm span ⁴	95.0	°C	ISO 75-2/Bf
1.8 MPa, unannealed, 3.20mm	53.9	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ⁵	56.0	°C	ISO 75-2/Af
Linear thermal expansion coefficient			
Flow: -40 to 40°C	1.0E-4	cm/cm/°C	ASTM E831
Flow: -40 to 40°C	1.4E-4	cm/cm/°C	ISO 11359-2
Lateral: -40 to 40°C	9.7E-5	cm/cm/°C	ASTM E831
Lateral: -40 to 40°C	1.7E-4	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+3	ohms	ASTM D257
Volume Resistivity	1.0E+4	ohms · cm	ASTM D257
Shielding Effectiveness (3.00 mm)	50 - 65	dB	Internal method
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Rear Temperature	204 - 216	°C	
Middle Temperature	232 - 243	°C	
Front Temperature	260 - 271	°C	
Processing (Melt) Temp	232 - 249	°C	
Mold Temperature	32.2 - 54.4	°C	
Back Pressure	0.172 - 0.344	MPa	
Screw Speed	25 - 50	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		
5.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

