

Grivory® HT2VZ-15H

Polyamide 6T/66 Copolymer

EMS-GRIVORY

Message:

Grivory® HT2VZ-15H is a Polyamide 6T/66 Copolymer (Nylon 6T/66) material filled with 15% glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America for injection molding.

Important attributes of Grivory® HT2VZ-15H are:

Flame Rated

Chemical Resistant

Heat Resistant

Impact Resistant

Typical applications include:

Electrical/Electronic Applications

Automotive

Appliances

Engineering/Industrial Parts

Tools

General Information				
Filler / Reinforcement		Glass Fiber,15% Filler by Weight		
Features		Alcohol Resistant		
		Aromatic		
		High Heat Resistance		
		High Impact Resistance		
Uses		Appliance Components		
		Automotive Applications		
		Automotive Interior Parts		
		Cell Phones		
		Connectors		
		Electrical/Electronic Applications		
		Engineering Parts		
		Hydraulic Applications		
		Pneumatic Applications		
		Power/Other Tools		
Forms		Granules		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.24	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	0.90	--	%	
Flow	0.40	--	%	
Water Absorption				ISO 62

Saturation, 23°C	5.5	--	%	
Equilibrium, 23°C, 50% RH	2.0	--	%	
Hardness	Dry	Conditioned	Unit	Test Method
Shore Hardness (Shore D, 15 sec)	84	82		ISO 868
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	6000	6000	MPa	ISO 527-2
Tensile Stress (Break)	125	100	MPa	ISO 527-2
Tensile Strain (Break)	3.0	3.5	%	ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	5.0	5.0	kJ/m ²	
23°C	10	10	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	45	40	kJ/m ²	
23°C	65	55	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
1.8 MPa, Unannealed	265	--	°C	ISO 75-2/A
8.0 MPa, Unannealed	100	--	°C	ISO 75-2/C
Maximum Use Temperature				Internal Method
Long Term	140	--	°C	
Short Term	240	--	°C	
ISO Type	PA 6T/66, MH, 12-060, GF15	--		ISO 1874
Melting Temperature ¹	310	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow	3.0E-5	--	cm/cm/°C	
Transverse	7.5E-5	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	--	1.0E+12	ohms	IEC 60093
Volume Resistivity	1.0E+12	1.0E+12	ohms·cm	IEC 60093
Electric Strength	33	32	kV/mm	IEC 60243-1
Comparative Tracking Index	--	575	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flammability Classification (0.800 mm)	HB	--		IEC 60695-11-10, -20
NOTE				
1.	10°C/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

