

PULSE™ GX50

PC/ABS Engineering Resin

Trinseo

Message:

PULSE GX50 is a very low gloss appearance engineering resins give exceptional impact strength even at low temperature and have sufficient heat resistance for the majority of automotive interior components. This resin provides excellent flow, has low odor & VOC values and is self colorable. Applications: PULSE GX50 is used in a wide range of applications where low gloss appearance and low temperature toughness is required.

General Information			
Features	Good Toughness		
	High Flow		
	High Heat Resistance		
	High Impact Resistance		
	Low Gloss		
	Low Temperature Impact Resistance		
	Low to No Odor		
	Low VOC		
Uses	Automotive Applications		
	Automotive Interior Parts		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	1.09	g/cm ³	ISO 1183/B
Melt Mass-Flow Rate (MFR) (260°C/5.0 kg)	12	g/10 min	ISO 1133
Molding Shrinkage	0.40 to 0.70	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2000	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	43.0	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	80	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	50	kJ/m ²	
23°C	50	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	93.0	°C	ISO 75-2/A
Vicat Softening Temperature	109	°C	ISO 306/B50
Flammability	Nominal Value	Unit	Test Method
Carbon Emission	10.0	µg/g	VDA 277
Injection	Nominal Value	Unit	

Processing (Melt) Temp	255 to 275	°C
Mold Temperature	70.0 to 80.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

