

Delas 175

Polyvinyl Chloride + NBR
Shanghai Lin Gen Rubber Materials Co., Ltd.

Message:

Delas 175 is a PVC NBR material. This product is available in the Asia-Pacific region and is processed by extrusion or injection molding. The main characteristics of Delas 175 are: chemical resistance.
The typical application field of Delas 175 is: wire and cable

General Information	
Features	Oil resistance
Uses	Wire and cable applications
Processing Method	Extrusion
	Injection molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.27	g/cm³	ASTM D792
Molding Shrinkage - Flow	1.5	%	ASTM D955

Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 5 sec)	75		ASTM D2240

Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	12.0	MPa	ASTM D412
Tensile Elongation (Break)	430	%	ASTM D412
Tear Strength	36.0	kN/m	ASTM D624
Compression Set (70°C)	66	%	ASTM D395

Additional Information	Nominal Value	Unit	Test Method
Operating Temperature	-26 - 80	°C	ASTM D746
Tear Permanent Deformation	76	%	ASTM D412

Injection	Nominal Value	Unit
Drying Temperature	80	°C
Drying Time	4.0	hr
Rear Temperature	140 - 150	°C
Middle Temperature	150 - 160	°C
Front Temperature	160 - 170	°C
Nozzle Temperature	170 - 180	°C
Mold Temperature	10 - 50	°C
Back Pressure	0.0700 - 1.00	MPa
Screw Speed	100 - 200	rpm

Extrusion instructions
Feed Zone: 140 - 150 °CFeed Section : 150 - 160 °CMetering Section: 160 - 170 °CFront Temperature: 170 - 180 °CMold Temperature: 170 - 180 °CFilter: 20-60 mesh

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

