

# ARLEN™ C430N

Polyamide 6T  
Mitsui Chemicals, Inc.

## Message:

ARLEN™ C430N by Mitsui Chemicals is a modified polyamide 6T reinforced with 30% glass fiber. Possesses high dimensional stability, high melting point, high rigidity and minimum water absorption. Exhibits good chemical and heat resistance. Is suitable for processing by injection molding. ARLEN™ C430N is recommended for electrical & electronic parts including connectors, jacks, switches and power supply terminals. Complies with UL 94 V-0 flame rating.

- Features:
- High dimensional stability
  - High melting point
  - High rigidity
  - Minimum water absorption
  - Good chemical and heat resistance
  - Flame retardant

Applications:  
Electrical and electronic parts including: connectors, jacks, switches, and power supply terminals.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Additive	Flame retardancy		
Features	Good Heat Resistance		
	High Dimensional Stability		
	Rigidity, high		
	Good chemical resistance		
	Low or no water absorption		
Uses	Flame retardancy		
	Electrical/Electronic Applications		
	Switch Connector		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.66	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage			ASTM D955
Flow	0.30	%	ASTM D955
Transverse flow	0.70	%	ASTM D955
Water Absorption (23°C, 24 hr, 65%r.h)	2.0	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	95		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	170	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	11400	MPa	ASTM D790

Flexural Strength	250	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	85	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	295	°C	ASTM D648
Glass Transition Temperature	85.0	°C	
Melting Temperature	310	°C	
Linear thermal expansion coefficient			ASTM E831
Flow	1.2E-5	cm/cm/°C	ASTM E831
Lateral	9.2E-5	cm/cm/°C	ASTM E831
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257
Dielectric Strength	26	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	4.00		ASTM D150
Dissipation Factor (1 MHz)	0.013		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT