DynaPath[™] C1430CF

Polybutylene Terephthalate

Polymer Dynamix

Message:

Features: Electrical conductivity Easy to mold Great surface appearance Applications: Automotive Industrial Electrical/Electronics

General Information					
Filler / Reinforcement	Carbon Fiber,30% Filler b	Carbon Fiber,30% Filler by Weight			
Features	Conductive				
	Good Processability				
	Good Surface Finish				
Uses	Automotive Applications	Automotive Applications			
	Electrical/Electronic Applications				
	Industrial Applications				
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	1.44	g/cm³	ASTM D792		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Strength (Yield)	162	MPa	ASTM D638		
Tensile Elongation (Break)	1.4	%	ASTM D638		
Flexural Modulus	15900	MPa	ASTM D790		
Elovural Strongth	252	MDa			

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.44	g/cm³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	162	МРа	ASTM D638
Tensile Elongation (Break)	1.4	%	ASTM D638
Flexural Modulus	15900	МРа	ASTM D790
Flexural Strength	252	МРа	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	48	J/m	ASTM D256
Unnotched Izod Impact (23°C, 3.18 mm)	450	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8			
MPa, Unannealed, 3.20 mm)	213	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

