

SCHULAMID® 66 RBL 2500 BLACK

Polyamide 66
A. Schulman Europe

Message:
25% glass fiber reinforced PA 66, Recycled Grade

General Information				
Filler / Reinforcement		Glass fiber reinforced material, 25% filler by weight		
Processing Method		Injection molding		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.31	--	g/cm ³	ISO 1183/A
Viscosity Number	136	--	cm ³ /g	ISO 307
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	8000	5200	MPa	ISO 527-2/1A/1
Tensile Stress (Break)	145	92.0	MPa	ISO 527-2/1A/5
Tensile Strain (Break)	2.5	7.7	%	ISO 527-2/1A/5
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	6.3	--	kJ/m ²	ISO 179/1eA
23°C	7.3	10	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	40	--	kJ/m ²	ISO 179/1eU
23°C	43	65	kJ/m ²	ISO 179/1eU
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, not annealed	> 250	--	°C	ISO 75-2/Bf
1.8 MPa, not annealed	238	--	°C	ISO 75-2/Af
Additional Information				

干燥
1.)
Not for use in food contact applications2.)
Not for use in medical or pharmaceutical applications

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

