

Dynacom 104-G30

Polybutylene Terephthalate

Dynachem Co. Ltd.

Message:

Dynacom 104-G30 is a Polybutylene Terephthalate (PBT) material. It is available in Asia Pacific. Primary attribute of Dynacom 104-G30: Flame Rated.

General Information			
UL YellowCard	E164708-224847		
UL File Number	E164708		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.62	g/cm ³	ASTM D792
Molding Shrinkage - Flow ¹	0.30 to 1.0	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.070	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ²	124	MPa	ASTM D638
Tensile Elongation ³ (Break)	3.0	%	ASTM D638
Flexural Modulus ⁴	8800	MPa	ASTM D790
Flexural Strength ⁵	186	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm)	69	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	215	°C	
1.8 MPa, Unannealed	205	°C	
RTI Elec	125	°C	UL 746
RTI Imp	125	°C	UL 746
RTI Str	125	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	2.5	ohms · cm	ASTM D257
Dielectric Strength (1.00 mm)	29	kV/mm	ASTM D149
Arc Resistance	120	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.0313 mm)	V-0		UL 94
NOTE			
1.	Thickness: Thickness: 2 to 3 mm		
2.	5.0 mm/min		
3.	5.0 mm/min		
4.	3.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

