

Dugdale PVC Flexible Injection Molding - Shore A 56 Compound

Flexible Polyvinyl Chloride

Dugdale Plc

Message:

Dugdale PVC Flexible Injection Molding - Shore A 56 Compound is a Flexible Polyvinyl Chloride product. It can be processed by injection molding and is available in Europe.

Characteristics include:

RoHS Compliant

Good Flexibility

General Information			
Features	Good Flexibility		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.48	g/cm ³	BS 2782 620A
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	56		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus - 100% Secant	6.12	MPa	BS 2782 320A
Tensile Strength	8.74	MPa	BS 2782 320A
Tensile Elongation (Break)	240	%	BS 2782 320A
Thermal	Nominal Value	Unit	Test Method
Cold Flexibility	-25	°C	BS 2782 150B
Softening Range	46.0		BS 2782 365A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT