

REXtac® APAO RT 3360

Polyalphaolefin
Huntsman Corporation

Message:
Ethylene copolymer

General Information			
Features	Copolymer amorphous		
Agency Ratings	FDA 21 CFR 175.105		
RoHS Compliance	Contact manufacturer		
Forms	Blank		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.860	g/cm ³	ASTM D792
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	-29.0	°C	DSC
Fill Analysis	Nominal Value	Unit	
Melt Density (190°C)	0.740	g/cm ³	
Additional Information			

Melt Viscosity, ASTM D3236, 300°F: 41000 cpsMelt Viscosity, ASTM D3236, 325°F: 12000 cpsMelt Viscosity, ASTM D3236, 350°F: 8400 cpsMelt Viscosity, ASTM D3236, 375°F: 6000 cpsMelt Viscosity, ASTM D3236, 400°F: 4300 cpsNeedle Penetration, ASTM D1321, 25°C: 2.0 mmSoftening Point by Ring and Ball, ASTM E28: 285°Fflexibility Failure Temp., 0.125" plaque thickness, 0.50" bend radius, Huntsman Method: -20°FFlashpoint, COC, ASTM D93: >450°F

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

