# Trilene FreeFlow™ CP80

### Ethylene Propylene Copolymer

Lion Copolymer, LLC

#### Message:

A Free-Flowing Ethylene-Propylene Low Molecular Weight Polymer on Silicon Dioxide

Trilene FreeFlow CP80 is a free-flowing polymer made by combining Trilene liquid polymer and silica. The blend is nominally 68% ethylene-propylene copolymer and 32% silica. It is available as a dry, free-flowing powder that is easy to measure, store, and transfer. It incorporates quickly and thoroughly into various elastomer systems, and gives quality and processing advantages when compared to neat polymer. Trilene FreeFlow CP80 is effective in EPDM, BR, NR, SBR and other elastomers.

General Information			
Filler / Reinforcement	Silica gel filler, 32% filler by weight		
Features	Low molecular weight		
	Workability, good		
Uses	Mixing		
Appearance	White		
	brownish yellow		
Forms	Powder		
Physical	Nominal Value	Unit	
Specific Gravity	1.05	g/cm <sup>3</sup>	
Molecular weight-Viscosity Average	8000		
Volatile Matter (100°C)		%	
Additional Information			
Ethylene/Pronylene: 15/55			

Ethylene/Propylene: 45/55

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

