

Sinvicomp SSZ5706

Flexible Polyvinyl Chloride

Teknor Apex Asia Pacific PTE. LTD.

Message:

SINVICOMP SSZ5706 is a flexible polyvinyl chloride material. This product is available in the Asia-Pacific region and is processed by extrusion. The main features of SINVICOMP SSZ5706 are: ROHS certification.
The typical application field of SINVICOMP SSZ5706 is: wire and cable

General Information			
Uses	Electrical wire sheath material		
RoHS Compliance	RoHS compliance		
Forms	Particle		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity ¹	1.47	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	84		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	16.0	MPa	IEC 811-1-1
Tensile Elongation (Break)	250	%	IEC 811-1-1
Aging	Nominal Value	Unit	Test Method
Changes in mechanical properties after hot air aging test, 168 hr ²			IEC 60811
Tensile strength change	10	%	IEC 60811
Change in tensile elongation	10	%	IEC 60811
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity (20°C)	1.0E+13	ohms·cm	BS 2782 230A
Additional Information	Nominal Value	Unit	Test Method
Loss of Mass - Oven Ageing Condition @ 80 ± 2°C for 7 days	1.40	mg/cm ²	IEC 811-3-2
Typical temperature profile for SINVICOMP compound is from 160°C to 180°C. The optimum temperatures depend on the type of machine as well as screw design being used to process SINVICOMP. Feeding zone: 160°C Mixing zone: 160°C~170°C Metering zone: 170°C~180°C Nozzle/Die Zone: 180°C			
NOTE			
1.	@ 23°C		
2.	@ 80 ± 2°C		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

