

Hylex® P1303L2 HB

Polycarbonate

Entec Polymers

Message:

POLYCARBONATE, UV STABILIZED, LOW MELT FLOW, MOLD RELEASE

General Information			
Additive	UV stabilizer		
Features	Good UV resistance		
	Low liquidity		
	Good demoulding performance		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	2.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.50 - 0.70	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield, 23°C	61.0	MPa	ASTM D638
Fracture, 23°C	57.9	MPa	ASTM D638
Tensile Elongation			ASTM D638
Yield, 23°C	6.0	%	ASTM D638
Fracture, 23°C	96	%	ASTM D638
Flexural Modulus (23°C)	2330	MPa	ASTM D790
Flexural Strength (23°C)	96.9	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	810	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	131	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT