

POCAN® B 3235 POS151 000000

Polybutylene Terephthalate

LANXESS GmbH

Message:

PBT, 30 % glass fibres, injection moulding, UV-stabilized

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	UV Stabilizer		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
	1.55		
Density (23°C)	1.55	g/cm ³	ISO 1183
Apparent Density	0.70	g/cm ³	ISO 60
Melt Volume-Flow Rate (MVR) (260°C/2.16 kg)	17.0	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 2577
Across Flow : 260°C, 2.00 mm ¹	1.1	%	
Across Flow : 120°C, 4 hr, 2.00 mm ²	0.20	%	
Flow : 260°C, 2.00 mm ³	0.40	%	
Flow : 120°C, 4 hr, 2.00 mm ⁴	0.20	%	
Water Absorption			ISO 62
	0.40		
Saturation, 23°C	0.40	%	
	0.10		
Equilibrium, 23°C, 50% RH	0.10	%	
Viscosity Number (Reduced Viscosity)	95.0	ml/g	ISO 1628
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness	190	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
23°C	9500	MPa	ASTM D638
23°C	9800	MPa	ISO 527-2/1

Tensile Strength			
Break, 23°C	133	MPa	ASTM D638
Break, 23°C	140	MPa	ISO 527-2/5
Tensile Elongation			
Break, 23°C	2.5	%	ASTM D638
Break, 23°C	2.9	%	ISO 527-2/5
Tensile Creep Modulus			
1 hr	9800	MPa	
1000 hr	8900	MPa	
Flexural Modulus			
23°C	7600	MPa	ASTM D790
23°C ⁵	9800	MPa	ISO 178/A
Flexural Strength			
23°C	190	MPa	ASTM D790
23°C ⁶	225	MPa	ISO 178/A
Flexural Strain at Flexural Strength ⁷ (23°C)	3.4	%	ISO 178/A
Burning Behavior ⁸	passed		ISO 3795
Electrolytical Corrosion (23°C)	A 1		IEC 60426
ISO Shortname	PBT,GHLMR,09-100,GF30		ISO 7792
	0.0 to 0.020		
Residual Moisture Content	0.0 to 0.020	%	Karl Fisher
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	< 10	kJ/m ²	
23°C	10	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	60	kJ/m ²	
23°C	65	kJ/m ²	
Notched Izod Impact Strength			ISO 180/1A
-40°C	< 10	kJ/m ²	
-30°C	< 10	kJ/m ²	
23°C	< 10	kJ/m ²	
Unnotched Izod Impact Strength			ISO 180/1U
-30°C	55	kJ/m ²	
23°C	55	kJ/m ²	
Multi-Axial Instrumented Impact Energy			ISO 6603-2
-30°C	2.50	J	
23°C	2.30	J	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			

0.45 MPa, Unannealed	220	°C	ISO 75-2/B
1.8 MPa, Unannealed	210	°C	ISO 75-2/A
8.0 MPa, Unannealed	165	°C	ISO 75-2/C
Vicat Softening Temperature	215	°C	ISO 306/B50
Ball Pressure Test (215°C)	Pass		IEC 60695-10-2
Melting Temperature ⁹	225	°C	ISO 11357-3
CLTE			ISO 11359-2
Flow : 23 to 55°C	3.0E-5	cm/cm/°C	
Transverse : 23 to 55°C	1.1E-4	cm/cm/°C	
Thermal Conductivity (23°C)	0.26	W/m/K	ISO 8302
Electrical	Nominal Value	Unit	Test Method
Electric Strength (23°C, 1.00 mm)	29	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
23°C, 100 Hz	4.00		
23°C, 1 MHz	3.80		
Comparative Tracking Index (Solution A)	350	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.800 mm	HB		
1.60 mm	HB		
Glow Wire Flammability Index (2.00 mm)	650	°C	IEC 60695-2-12
Oxygen Index ¹⁰	20	%	ISO 4589-2
Injection	Nominal Value	Unit	Test Method
Drying Temperature - Circulation Dryer	120	°C	
	4.0 to 8.0		
Drying Time - Circulation Dryer	4.0 to 8.0	hr	
Processing (Melt) Temp	250 to 270	°C	
Mold Temperature	80.0 to 100	°C	
NOTE			
1.	60x60x2mm, 80°C MT, 600 bar		
2.	60x60x2mm		
3.	60x60x2mm, 80°C MT, 600 bar		
4.	60x60x2mm		
5.	2.0 mm/min		
6.	2.0 mm/min		
7.	2 mm/min		
8.	US-FMVSS302		
9.	10°C/min		
10.	Procedure A		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

