

Zytel® 101L NC010

NYLON RESIN
DuPont Performance Polymers

Message:
Unreinforced Polyamide 66

General Information				
UL YellowCard		E41938-100726136	E41938-234369	
Additive		Mold Release		
Agency Ratings		UL Unspecified Rating		
Forms		Pellets		
Processing Method		Injection Molding		
Multi-Point Data		Shear Modulus vs. Temperature (ISO 11403-1)		
		Shear Stress vs. Shear Rate (ISO 11403-1)		
		Tensile Modulus vs. Temperature (ISO 11403-1)		
		Viscosity vs. Shear Rate (ISO 11403-2)		
Part Marking Code (ISO 11469)		>PA66<		
Resin ID (ISO 1043)		PA66		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.14	--	g/cm³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	1.4	--	%	
Flow	1.4	--	%	
Water Absorption				ISO 62
23°C, 24 hr, 2.00 mm	8.5	--	%	
Equilibrium, 23°C, 2.00 mm, 50% RH	2.6	--	%	
Viscosity Number	150	--	cm³/g	ISO 307
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness				ISO 2039-2
M-Scale	79	59		
R-Scale	121	108		
Ball Indentation Hardness (H 358/30)	180	85.0	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	3100	1400	MPa	ISO 527-2
Tensile Stress (Yield)	82.0	55.0	MPa	ISO 527-2
Tensile Strain (Yield)	4.5	25	%	ISO 527-2
Nominal Tensile Strain at Break	25	> 50	%	ISO 527-2

Tensile Creep Modulus				ISO 899-1
1 hr	--	1400	MPa	
1000 hr	--	820	MPa	
Flexural Modulus	2800	1200	MPa	ISO 178
Films	Dry	Conditioned	Unit	Test Method
Tensile Elongation - MD (Yield)	4.5	--	%	ISO 527-3
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	4.5	3.0	kJ/m ²	
23°C	5.5	15	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	400 kJ/m ²	No Break		
23°C	No Break	No Break		
Notched Izod Impact Strength				ISO 180/1A
-40°C	5.5	--	kJ/m ²	
-30°C	5.5	3.0	kJ/m ²	
23°C	5.5	12	kJ/m ²	
Unnotched Izod Impact Strength				ISO 180/1U
-30°C	300	--	kJ/m ²	
23°C	No Break	No Break		
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	200	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	70.0	--	°C	ISO 75-2/A
Glass Transition Temperature ¹	60.0	--	°C	ISO 11357-2
Vicat Softening Temperature	240	--	°C	ISO 306/B50
Melting Temperature ²	262	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow	1.0E-4	--	cm/cm/°C	
Transverse	1.1E-4	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+12	--	ohms	ASTM D257
Volume Resistivity	1.0E+14	1.0E+12	ohms·cm	IEC 60093
Electric Strength	32	28	kV/mm	IEC 60243-1
Dielectric Constant				
100 Hz	4.00	--		ASTM D150
1 kHz	3.90	--		ASTM D150

1 MHz	3.60	--		ASTM D150
100 Hz	3.80	11.0		IEC 60250
1 MHz	3.50	4.00		IEC 60250
Dissipation Factor				IEC 60250
100 Hz	8.0E-3	0.21		
1 MHz	0.018	0.075		
Comparative Tracking Index (CTI)	PLC 0	--		UL 746
Comparative Tracking Index	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flammability Classification				IEC 60695-11-10, -20
0.710 mm	V-2	--		
1.50 mm	V-2	--		
Oxygen Index	28	--	%	ISO 4589-2
Fogging - G-value (condensate)	4.0E-4	--	g	ISO 6452
Specific Heat Capacity of Melt	2790	--	J/kg/°C	
Thermal Conductivity of Melt	0.16	--	W/m/K	
Effective Thermal Diffusivity	0.0500	--	cSt	
Emission of Organic Compounds	10.0	--	µgC/g	VDA 277
Odor	3.5	--		VDA 270
Fill Analysis	Dry	Conditioned	Unit	Test Method
Melt Density	0.970	--	g/cm ³	
NOTE				
1.	10°C/min			
2.	10°C/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT