

TECHNO MUH E1500

Acrylonitrile Butadiene Styrene

Techno Polymer Co, Ltd.

Message:

TECHNO MUH E1500 is an Acrylonitrile Butadiene Styrene (ABS) product. It can be processed by injection molding and is available in Asia Pacific or North America. Primary characteristic: heat resistant.

General Information			
Features	High Heat Resistance		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.05	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (240°C/10.0 kg)	8.0	g/10 min	ISO 1133
Molding Shrinkage	0.50 to 0.80	%	ISO 294-4
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	108		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	50.0	MPa	ISO 527-2
Flexural Modulus	2410	MPa	ISO 178
Flexural Stress	76.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	11	kJ/m²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	99.0	°C	ISO 75-2/B
Injection	Nominal Value	Unit	
Drying Temperature	100 to 110	°C	
Drying Time	2.0 to 5.0	hr	
Rear Temperature	220 to 270	°C	
Middle Temperature	220 to 270	°C	
Front Temperature	220 to 270	°C	
Mold Temperature	40.0 to 80.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

